Waterproof Fabric Technical Details

Technical Data for Waterproof, Flame Retardant Mattress Ticking



Fabric Composition: 100% Transfer printed polyester, impregnated

and multi-coated with microporous polymers

and flame retardant.

Fabric Construction: 4/1 Twill Weave.

Product Weight & Presentation: BS EN 12127 1998: 280gm2 +/- 10%

Flame Retardant: BS 7175 (1989) Crib 7

Waterproof: Hydrostatic Head BS 3424 Part 26 1990

Method 29A/B >1mt

Tear Strength: BS EN ISO 13937-3: 2000 WARP: 30N WEFT:

80N +/- 10%

Tensile Strength: BS EN ISO 13934-1 1999 WARP: 490N WEFT:

490N +/-

Abrasion Resistance: BS EN ISO 12945-1 2001 > 50.000 NO PILLLING.

Urea Resistance: BS 3424, Part 19, No Deterioration after 24 hours

urea soak.

Antimicrobial: ASTM E 2149-01 Will not support microbial

growth including:

- Aspergillus Niger

- F-Coli

- Altinata

- Salmonella

- Penicillium

- Staphylococcus Aureus

- Cladosporium Herbarism

- M.R.S.A.

Hypo-Allergenic: Forms effective barrier against bed mites etc

Breathable: Moisture Vapour Permeable

COLD WATER - GRADE 5 Colour Fastness: BS EN ISO 105 E01: 1996 WARP: WET RUB= GR. 5 /

BS EN ISO 105 X12: 2002

Dry Rub: GR. 5

WEFT: WET RUB= GR. 5 / DRY RUB= GR. 5

Care & Maintenance: SOILING 1. Routine soap and warm water sponging

is effective for ordinary use.

2. Fresh stains both water & oil based are easily removed using most water based household

spray cleaning agents.

3. A half cup of household bleach for 5 litres

of water can also be used as a useful disinfectant.

4. Best cleaning method is 'wipe and dry' technique.

Full immersion not recommended.

5. DO NOT DRY CLEAN!